



AVF Paints

Antilliaanse Verffabriek B.V.

P.O.BOX 3944 • Asteroidenweg z/n • Curaçao • Netherlands Antilles • Tel.Office: (599-9) 736-5866 • Fax: (599-9) 736-5048

Ambiance®

Premium Quality Low Odor Interior Paint
(Line 217)

Description

Ambiance® is a premium quality, zero VOC* low odor paint ideal for painting of occupied spaces (interior use). Ambiance® is recommended for new or previously painted plaster and masonry. It will provide a beautiful finish on walls and ceilings.

Product Information

Technical Data

Vehicle Type
Pigment Type
Solids by Volume
Theoretical Coverage

Depending on surface texture and porosity

Recommended Film Thickness

Wet

Dry

Dry Time @ 25°C

To Touch

To Handle

To Recoat

Dries By

Flash Point

Gloss

Thin with

Clean up Thinner

Weight Per Gallon

Ambiance®

A Vinyl-Acetate Copolymer Emulsion

Titanium Dioxide

28%

30m²/US Gallon @ 35µm DFT

125µm

35µm

½ Hour

½ Hour

1 hours

Evaporation / Coalescence

-

Flat

Water (maximum of 5% by volume)

Water

5.4 kg/gallon

Recommended For

Concrete, plaster, asbestos, drywall etc. on interior surfaces.

Color

White and base for AVF Paints color system.

Applicable by

Brush, roller or airless spray.

* (Depending on color)



AVF Paints

Antilliaanse Verffabriek B.V.

P.O.BOX 3944 • Asteroidenweg z/n • Curaçao • Netherlands Antilles • Tel.Office: (599-9) 736-5866 • Fax: (599-9) 736-5048

Packing

1 US Gallon (3.785 Liters).

Clean up

Clean brushes and rollers with clean water after use. Spray equipment should be cleaned with water and given a final rinse with White Spirit.

Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

Remark

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting. Metal parts such as nail heads, should be wiped clean and primed with the appropriate metal primer. New plasterwork (PH greater than 10) has to cure properly for at 30 days and preferably 90 days prior to painting, if it is possible should be primed with one (1) or two (2) coats of Wall Sealer. If mildew is present remove all traces with a solution of Ammonia. CAUTION: use protective clothing and work goggles when applying Ammonia solution. WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE.

.....
Limitation of liability: The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Antilliaanse Verffabriek B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Antilliaanse Verffabriek B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Antilliaanse Verffabriek B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.

Revision Feb/2015 AB