



AVF Paints

Antilliaanse Verffabriek B.V.

P.O.BOX 3944 • Asteroidenweg z/n • Curaçao • Netherlands Antilles • Tel.Office: (599-9) 736-5866 • Fax: (599-9) 736-5048

Aqualux Enamel

100% acrylic, odorless paint.
(Line 203)

Description

Aqualux Enamel is a high quality, water based, 100% acrylic paint in a semi gloss finish, for interior and exterior use. Aqualux Enamel provides optimal adhesion, and Colors retention with long lasting durability. Aqualux Enamel is quick drying and almost odorless. Aqualux Enamel is suitable for the decoration and protection of windows, doors, wood furniture, air-dried walls, fiber building boards, brick, masonry, stucco and cinder block. Aqualux Enamel is very easily applied by brush, roller or airless spray.

Product Information

Technical Data

Vehicle Type
Pigment Type
Solids by Volume
Theoretical Coverage
Depending on surface texture and porosity
Recommended Film Thickness
Wet
Dry
Dry Time @ 25°C
To Touch
To Handle
To Recoat
Dries By
Flash Point
Gloss
Thin with
Clean up Thinner
Weight Per Gallon

Aqualux Enamel

100% Acrylic
Titanium Dioxide
37%
34 m²/US Gallon @ 30µm DFT
90µm
30µm
½ Hours
1 Hours
2 hours
Evaporation / Coalescence
-
Satin Gloss
Water (max 2% by volume)
Water
4.62 kg/gallon

Recommended For

Hospitals and day care centers. Excellent for areas where a durable film is required as it can withstand repeated washing and mild scrubbing.

Color

Color card shades.



AVF Paints

Antilliaanse Verffabriek B.V.

P.O.BOX 3944 • Asteroidenweg z/n • Curaçao • Netherlands Antilles • Tel.Office: (599-9) 736-5866 • Fax: (599-9) 736-5048

Applicable by

Brush, roller and airless spray.

Packing

¼ US Gallon (0.945 Liters).

1 US Gallon (3.785 Liters).

Clean up

Clean brushes and rollers with clean water after use.

Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

Remark

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting. Metal parts such as nail heads, should be wiped clean and primed with the appropriate metal primer. New plasterwork (PH greater than 10) has to cure properly and should be primed with one (1) or two (2) coats of Wall Sealer. If mildew is present remove all traces with a solution of Ammonia. CAUTION: use protective clothing and work goggles when applying Ammonia solution. WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE. New plaster must be allowed to cure (30-60 days).

.....
Limitation of liability: The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Antilliaanse Verffabriek B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Antilliaanse Verffabriek B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Antilliaanse Verffabriek B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.