



AVF Paints

Antilliaanse Verffabriek B.V.

P.O.BOX 3944 • Asteroidenweg z/n • Curaçao • Netherlands Antilles • Tel.Office: (599-9) 736-5866 • Fax: (599-9) 736-5048

Comolux® Enamel

General purpose enamel.
(Line 100)

Description

Comolux® Enamel is an oxidative drying enamel based on a modified alkyd, possessing good weather resistance properties. Comolux® Enamel is applicable as finishing coat in all alkyd systems for wood and metal substrates.

Product Information

Technical Data

Vehicle Type
Pigment Type
Solids by Volume
Theoretical Coverage
Depending on surface texture and porosity
Recommended Film Thickness
Wet
Dry
Dry Time @ 25°C
To Touch
To Handle
To Recoat
Dries By
Flash Point
Gloss
Thin with

Clean up Thinner
Weight Per Gallon

Comolux® Enamel

Modified alkyd
Titanium Dioxide
48%
50 m²/US Gallon @ 30µm DFT

75µm
30µm

3 Hours
4 Hours
24 Hours
Evaporation / Oxidation
-
High gloss
Thinner #902
(for brush, roller applications max 5% by volume)
Thinner #995/#990
(for spray applications max 10% by volume)
Thinner #902
4.24 kg/gallon

Recommended For

Metal, equipment, machinery, marine exposures (above water), railings, piping, doors, cabinets, storage tanks, metal buildings, fences, general maintenance painting.

Color

Color card shades / AVF Paints color system.



AVF Paints

Antilliaanse Verffabriek B.V.

P.O.BOX 3944 • Asteroidenweg z/n • Curaçao • Netherlands Antilles • Tel.Office: (599-9) 736-5866 • Fax: (599-9) 736-5048

Applicable by

Brush, roller or airless spray.

Packing

1/16 US Gallon (0.236 Liters).

¼ US Gallon (0.945 Liters).

1 US Gallon (3.785 Liters).

5 US Gallon (18.93 Liters). *Special request*

Clean up

Clean brushes and rollers thinner #902 after use.

Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

Remark

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting. Metal parts such as nail heads, should be wiped clean and primed with the appropriate metal primer. New plasterwork (PH greater than 10) has to cure properly and should be primed with one (1) or two (2) coats of Wall Sealer. If mildew is present remove all traces with a solution of Ammonia. CAUTION: use protective clothing and work goggles when applying Ammonia solution. WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE. New plaster must be allowed to cure (30-60 days).

.....
Limitation of liability: The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Antilliaanse Verffabriek B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Antilliaanse Verffabriek B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Antilliaanse Verffabriek B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.