



AVF Paints

Antilliaanse Verffabriek B.V.

P.O.BOX 3944 • Asteroidenweg z/n • Curaçao • Netherlands Antilles • Tel.Office: (599-9) 736-5866 • Fax: (599-9) 736-5048

Estuco (interior)

Leaving a smooth surface.
(Line 203)

Description

Estuco (interior) may be used for coating walls and ceilings and to cover less visually appealing construction materials such as concrete, cinder block and brick leaving a smooth surface. Estuco (interior) can also be used as a decorative finish.

Product Information

Technical Data

Estuco (interior)

Vehicle Type	100% Acrylic
Pigment Type	Titanium Dioxide
Solids by Volume	-
Theoretical Coverage	4-6 m ² /US Gallon
<i>Depending on surface texture and porosity</i>	
Recommended Film Thickness	
Wet	-
Dry	-
Dry Time @ 25°C	
To Touch	1 Hours
To Handle	2 Hours
To Recoat	24 hours
Dries By	Evaporation
Flash Point	-
Gloss	-
Thin with	Water
Clean up Thinner	Water
Weight Per Gallon	6 kg/gallon

Recommended For

Concrete, cinder block and brick. Can also be used to seal joints between sheets of drywall, primarily in building construction.

Color

Off white.

Applicable by

Trowel.



AVF Paints

Antilliaanse Verffabriek B.V.

P.O.BOX 3944 • Asteroidenweg z/n • Curaçao • Netherlands Antilles • Tel.Office: (599-9) 736-5866 • Fax: (599-9) 736-5048

Packing

5 US Gallon (18.93 Liters).

Clean up

Clean brushes and rollers with clean water after use.

Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

Remark

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting. Metal parts such as nail heads, should be wiped clean and primed with the appropriate metal primer. New plasterwork (PH greater than 10) has to cure properly and should be primed with one (1) or two (2) coats of Wall Sealer. If mildew is present remove all traces with a solution of Ammonia. CAUTION: use protective clothing and work goggles when applying Ammonia solution. WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE. New plaster must be allowed to cure (30-60 days).

.....
Limitation of liability: The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Antilliaanse Verffabriek B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Antilliaanse Verffabriek B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Antilliaanse Verffabriek B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.