



AVF Paints

Antilliaanse Verffabriek B.V.

P.O.BOX 3944 • Asteroidenweg z/n • Curaçao • Netherlands Antilles • Tel.Office: (599-9) 736-5866 • Fax: (599-9) 736-5048

Textured Paint (Structuurverf)

Textured Paint can be used in just about any room in a home to accent furniture, hide stains or damage, or simply add some personality into a room.
(Line 209)

Description

Textured Paint is a physically drying paint containing specially selected filling materials based on a polyvinyl acetate emulsion. Textured Paint can be applied on interior and exterior surfaces. High or low texture will depend upon choice of tools.

Product Information

Technical Data

Vehicle Type
Pigment Type
Solids by Volume
Theoretical Coverage
Depending on surface texture and porosity
Recommended Film Thickness
Wet
Dry
Dry Time @ 25°C
To Touch
To Handle
To Recoat
Dries By
Flash Point
Gloss
Thin with
Clean up Thinner
Weight Per Gallon

Textured Paint

Polyvinyl acetate
Titanium Dioxide
52%
8 m²/US Gallon @ 200µm DFT
390µm
200µm
4 Hours
14 Hours
24 hours
Evaporation
-
Satin finish
No thinning
Water
5.37 kg/gallon

Recommended For

Paneling, Concrete Blocks, Cracking Plaster, Finished or Unfinished Drywall, Raw Wood and Cement Particle board. Our assortment contains 3 (three) different types of textured paint;
Structuurverlite, Magnatex structuur, Spuitstructuur 1-2 mm

Color

White, can be painted over in desired color.



AVF Paints

Antilliaanse Verffabriek B.V.

P.O.BOX 3944 • Asteroidenweg z/n • Curaçao • Netherlands Antilles • Tel.Office: (599-9) 736-5866 • Fax: (599-9) 736-5048

Applicable by

Brush, roller or airless spray.

Packing

1 US Gallon (3.785 Liters).

5 US Gallon (18.93 Liters).

Clean up

Clean brushes and rollers with clean water after use.

Safety Information

Use with adequate ventilation. Avoid contact with eyes and repeated contact with skin. Wear eye protection and gloves during application.

First Aid

If you experience difficulty in breathing, leave area immediately. In case of eye contact, flush with plenty of water. In case of ingestion, do not induce vomiting. Get medical help immediately.

Remark

Surface must be clean, free of loose paint, chalk, grease and dust. Patch damaged areas and chalk open joints. If any areas are peeled, cracked or blistered, the condition causing this must be corrected for successful painting. Metal parts such as nail heads, should be wiped clean and primed with the appropriate metal primer. New plasterwork (PH greater than 10) has to cure properly and should be primed with one (1) or two (2) coats of Wall Sealer. If mildew is present remove all traces with a solution of Ammonia. CAUTION: use protective clothing and work goggles when applying Ammonia solution. WARNING! Scraping or sanding of old paint may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS. PREGNANT WOMEN SHOULD AVOID EXPOSURE. New plaster must be allowed to cure (30-60 days).

.....
Limitation of liability: The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Antilliaanse Verffabriek B.V., whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. Antilliaanse Verffabriek B.V. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Antilliaanse Verffabriek B.V. does therefore not accept any liability arising from loss or injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is the user's responsibility to ensure that this sheet is the current prior to using the product. The English text of this document shall prevail over any translation thereof.